

	VITAL TECHNICAL SDN. BHD.	 
	Technical Data Sheet	
	VT-768 Ultimate D3 Wood Glue	

Issuance date: 03/10/2024

Revision date:

Revision No.: -

Product Specification:			
Appearance	:	Viscous liquid	
Solid content	:	48.0 - 50.0%	
pH	:	3.0 - 4.0	
Viscosity (Brookfield LV 3 @ 5rpm)	:	11,000 - 15,000 cps	
Specific Gravity	:	1.05 - 1.10	
Colour	:	White (Wet) Clear (Dry)	
Wet tack	:	Aggressive	
Flammability	:	Non-flammable	
Shelf life	:	24 months	
Features	:	Water-resistant D3 Indoor & outdoor use Easy to spread High bond strength Fast curing Forms thin gapless layer when set Non-toxic, solvent free and low odour	
Packaging			
Product Code	Content	Inner Box	Carton
VT-768-125	125 g bottle	12	144
VT-768-250	250 g bottle	12	72
VT-768-500	500 g bottle	-	24

Product Description:

An ultimate D3-grade wood glue, specially formulated for woodworking applications that require resistance to short-term submersion. It offers fast setting, superior bonding strength, and versatility with various porous substrates for both indoor and outdoor use. It is non-toxic, solvent-free, and easy to clean up with water.

Applications:

Suitable for indoor and outdoor wood joining, furniture repair, wooden frames, and woodworking projects that require short-term submersion resistance. Not recommend for continuous submersion or use below the waterline.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Apply the adhesive on both surfaces if the material is porous. Press together firmly and leave to dry.
3. Replace cap after use and store in a cool, dry place.

Caution:

Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Storage:

Minimum of 24 months in tightly closed packing when stored in cool and dry place, below 30 °C.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.